Listing of Claims

- 1. (Currently Amended) A method for forming a polymer comprising initiating a polymerization of tertiary alkene monomers and vinyl aromatic hydrocarbon monomers, said vinyl aromatic hydrocarbon monomers having substituents of the formula R¹SiR²R³R⁴, wherein R¹ is optional and is a hydrocarbon or ether linking links the silicon and said vinyl aromatic and is selected from methylene group, divalent hydrocarbon group having more than 6 carbon atoms, or divalent hydrocarbon group comprising one or more ether functional groups provided that any ether oxygen and the silicon are connected via at least one carbon atom, and R², R³, and R⁴ are one or more of hydrogen, alkyl, and alkoxy, with the proviso that no more than two may be hydrogen or alkyl.
- (Original) The method of claim 1 wherein said polymerization is initiated by a cationic initiator system.
- 3. (Original) The method of claim 1 wherein said tertiary alkene is one or more of isobutylene, 2-methylbutene, 2-methylpentene, and 2-methylhexene.
- 4. (Currently Amended) The method of claim 1 wherein said R¹ is present and comprises a C1-C8 alkyl group and may optionally include one or more of an other group a methylene group, a divalent hydrocarbon group having 7 carbon atoms, a divalent hydrocarbon group having 8 carbon atoms, or a C₁-C₈ divalent hydrocarbon group comprising one or more other functional groups.
- 5. (Original) The method of claim 1 wherein said R², R³, and R⁴ are independently selected from one or more of hydrogen, C₁-C₁₀ alkyl groups, methoxy, ethoxy, propoxy, butoxy, pentoxy, and alkoxy groups with up to 10 carbons in the alkyl portion, with the proviso that no more than two be hydrogen or alkyl.
- 6. (Original) The method of claim 2 wherein said cationic initiator system comprises a Lewis acid and alkyl halide.

- 7. (Original) The method of claim 6 wherein said Lewis acid is selected from TiCl₄, BCl₃, AlCl₃, Et₂AlCl, EtAlCl₂, and mixtures thereof.
- 8. (Original) The method of claim 6 wherein said alkyl halide comprises one or more of α, α, α, α, α tetramethyl-1,4-benzenedimethyl chloride, t-butyl chloride, t-butyl bromide, 2-chloro-2-methylpentane, 2-bromo-2-methylpentane, 2-chloro-2-methylbutane, 2-chloro-2-phenylpropane, 2-bromo-2-phenylpropane, 1,3-(2-chloro-2-propyl)-5-t-butyl benzene, 1,3-(2-bromo-2-propyl)-5-t-butyl benzene and 2-bromo-2-methylbutane.
- 9. (Currently Amended) A method for forming a building sealant comprising: initiating cationic polymerization of tertiary alkene monomer units and vinyl aromatic hydrocarbon monomer units, said vinyl aromatic hydrocarbon monomer units having substituents of the formula R¹SiR²R³R⁴, wherein R¹ is optional and is a hydrocarbon or ether linking links the silicon and said vinyl aromatic and is selected from methylene group, divalent hydrocarbon group having more than 6 carbon atoms, or divalent hydrocarbon group comprising one or more ether functional groups provided that any ether oxygen and the silicon are connected via at least one carbon atom, and R², R³, and R⁴ are one or more of hydrogen, alkyl, and alkoxy, with the proviso that no more than two may be hydrogen or alkyl, to form a sealant polymer, and combining said sealant polymer with a hardener.
- 10. (Original) The method of claim 9 wherein said polymerization is cationic and includes a Lewis acid.
- 11. (Original) The method of claim 10 wherein said Lewis acid comprises TiCl₄, BCl₃, AlCl₃, Et₂AlCl, EtAlCl₂, and mixtures thereof.
- 12. (Currently Amended) The method of claim 9 wherein said said R¹ is present and comprises a C1-C8 alkyl group and may optionally include one or more of an ether group a methylene group, a divalent hydrocarbon group having 7 carbon atoms, a divalent

- hydrocarbon group having 8 carbon atoms, or a C_1 - C_8 divalent hydrocarbon group comprising one or more ether functional groups.
- 13. (Original) The method of claim 9 wherein said R², R³, and R⁴ are independently selected from one or more of hydrogen, C₁-C₁₀ alkyl groups, methoxy, ethoxy, propoxy, butoxy, pentoxy, and alkoxy groups with up to 10 carbons in the alkyl portion, with the proviso that no more than two be hydrogen or alkyl.
- 14. (Original) The method of claim 9 wherein said hardener comprises a tin or amine containing compound.
- 15. (Cancelled)
- 16. (Cancelled)
- 17. (Cancelled)
- 18. (Cancelled)
- 19. (Cancelled)
- 20. (New) A method for forming a polymer comprising initiating a polymerization of tertiary alkene monomers and vinyl aromatic hydrocarbon monomers, said vinyl aromatic hydrocarbon monomers having substituents of the formula SiR²R³R⁴, wherein the silicon is directly bonded to said vinyl aromatic and R², R³, and R⁴ are one or more of hydrogen, alkyl, and alkoxy, with the proviso that no more than two may be hydrogen or alkyl.